

## Fibrolith 25 mm stall ventilation panels / agro boards

WW wood-wool board in accordance with  
 DIN EN 13168,  
 homogen, cement-bound  
 Quality type WW WI dm / WW DI dm  
 Low flammability (B-s1, d0)  
 Non-smoldering  
 White cement, fine wool (approx. 2mm)  
 with large 11mm fibers, or straight edges



Properties:

- Wood-wool board, bound with cement
- Ecologically sound
- good sound absorption
- High vapor permeability



Promoting Sustainable  
 Forest Management  
[www.pefc.co.uk](http://www.pefc.co.uk)

Area of Application:

Wall and ceiling cladding in functional agricultural buildings.

Article master	Board thickness in mm	Heat transfer resistance RD m <sup>2</sup> K/W	Standard in mm		Weight in kg		Contents per pallet (2400 x 1200mm) (1200 x 1200mm)	
			Length	Width	per m <sup>2</sup>	per pallet	Piece	m <sup>2</sup>
2525 6090162025	25	0.33	2400	600	11.5	2,360/1,200	140/70	201.6/100.8
2525 6090162025	25	0.33	1200	600	11.5	760	70	50.4

Alternative length 2000 mm

straight edge




beveled edges (approx. 11 mm)



Image source: Moser Lüftungstechnik, Ried im Taunuskreis, Austria

## Laying instructions



for board sizes: 2400 x 600 mm, or 1200 x 600 mm  
on wooden slat sub-structures or CD profiles

Board strength in mm	Screws Dimensions/type
25	4.2 x 45

This technical information reflects the current level of our knowledge and experience. Subject to changes without prior notification. Please use the latest version of the product data sheet as levels of experience and knowledge are constantly developing. Please contact our office in the event of doubt. Examples of use described may not account for the specific circumstances of each individual case and we therefore accept no liability for them. Otherwise, only our General Terms of Sale, Delivery and Payment (latest version), of which you are aware, apply. Januar 2020

Fibrolith Dämmstoffe GmbH  
An der L83 · D-56746 Kempenich  
Tel.: +49 (0) 26 55 / 95 92-0  
Fax: +49 (0) 26 55 / 95 92-18  
E-Mail: info@fibrolith.de

Geschäftsführer: Christophe Beyer,  
Pierre-Etienne Bindschedler  
HRB Nr. 13079 - Amtsgericht Koblenz  
Sitz der Gesellschaft: Kempenich  
USt-ID-Nr.: DE 811413077

Commerzbank AG  
Frankfurt am Main  
IBAN: DE26 5008 0000 0380 0477 00  
SWIFT-BIC: DRES DE FF

[www.fibrolith.de](http://www.fibrolith.de)

**SOPREMA**  
GROUP